



## Description

A controlled expansion alloy consisting of approximately 51% Nickel, balance Iron; used in a wide variety of electronic applications, especially for glass seals.

AKA: Pernifer® 50 and Carpenter Glass Sealing® 52.

## Application

Glass to metal seals for electronic tubes, automotive and industrial lamps, and specialty hermetic devices.

### PHYSICAL PROPERTIES

|                        |                      |
|------------------------|----------------------|
| Density                | 8.3g/cm <sup>3</sup> |
| Specific gravity       | 8.3                  |
| Curie temperature      | 530°C                |
| Melting point          | 1427°C               |
| Electrical resistivity | 43 microhm-cm        |
| Thermal conductivity   | 18 W/mK              |
| Specific heat          | 0.5 J/g°C            |

### MECHANICAL PROPERTIES

|                       |          |
|-----------------------|----------|
| Tensile strength      | 517 MPa  |
| Yield strength        | 276 MPa  |
| Elongation            | 35%      |
| Hardness              | 80 HRB   |
| Modulus of elasticity | 159 kMPa |

### LINEAR COEFFICIENT OF PHYSICAL THERMAL EXPANSION

| Temperature °C | Temperature CTE (ppm/°C) |
|----------------|--------------------------|
| 30-300         | 10.1                     |
| 30-400         | 9.9                      |
| 30-450         | 9.7-10.2                 |
| 30-500         | 9.9                      |
| 30-550         | 10.0-10.5                |
| 30-600         | 10.8                     |
| 30-700         | 11.7                     |
| 30-800         | 12.5                     |
| 30-900         | 13.3                     |
| 30-1000        | 14.2                     |

## SPECIFICATIONS

|      |             |
|------|-------------|
| ASTM | F30         |
| MIL  | 1-23011 CL2 |
| AMS  | 1-23011 CL2 |
| UNS  | N14052      |

## CHEMISTRY

|                                   |         |
|-----------------------------------|---------|
| 28 Nickel<br><b>Ni</b><br>58.6934 | 50.5%   |
| 27 Cobalt<br><b>Co</b><br>58.933  | -       |
| 26 Iron<br><b>Fe</b><br>55.847    | Balance |
| <b>C</b>                          | 0.05%   |
| <b>Si</b>                         | 0.3%    |
| <b>S</b>                          | 0.025%  |
| <b>Cr</b>                         | 0.025%  |

## FORMS AVAILABLE:



Coil



Sheet



Plate



Rod



Bar



Wire

|                                      |                                     |                                   |
|--------------------------------------|-------------------------------------|-----------------------------------|
| 28<br>Nickel<br><b>Ni</b><br>58.6934 | 27<br>Cobalt<br><b>Co</b><br>58.933 | 26<br>Iron<br><b>Fe</b><br>55.847 |
|--------------------------------------|-------------------------------------|-----------------------------------|

## More than just metal

We're one of Europe's leading suppliers of premium quality refractory metals and alloys, soft magnetic alloys, and controlled expansion alloys. We hold a large stock of UK-certified, materials, all with full chain custody. With a deep technical understanding, comprehensive workshop facilities, and top accreditations, we help our customers get more from their materials.

### Knowledge and advice

Our team understands exactly how our products are made, how they will behave in different situations, and how they should perform. Their knowledge and expertise helps save time, effort and cost by ensuring that all materials are sourced, processed and tested to perform in the most effective way.

We partner with leading academic institutions and scientific organisations that add value to our service and help develop solutions to the challenges impacting our customers. We're keen to share these unique insights in order to deliver practical operational improvements.

### Workshop and machining

Our purpose-built facilities are centred around a fully equipped workshop designed to address almost any customer request:

- CNC Proturn RLX 1630 lathe for high precision rod and bar processing
- Saws to cut bars, plate and billets from Ø 2mm to Ø 270mm
- Guillotines for sheet and coil
- Grinding machinery
- De-coiler to check for imperfections before shipping
- Coil handling equipment to inspect product before dispatch
- Water jet and laser cutting
- Heat treatments

### Quality control

All orders are fully tested before shipping. Our state-of-the-art metrology lab features:

- Micrometers, verniers and gauges for all applications
- Surface roughness tester
- Straightness and roundness testing apparatus
- Magnetometers for measuring inductance, coercive and saturation
- Capabilities for evaluating properties such as CTE, tensile and elongation.

### Best practice

We are committed to continuous improvement, reflected in our achievement of internationally-recognised industry accreditations. These are the foundation of best practice and provide you with solid assurances of competence and integrity:

- **AS9120** certified – a top aerospace industry award.
- **Green Mark level 1** accreditation – an environmental certification that supports greater sustainability.
- **JOSCAR** (the Joint Supply Chain Accreditation Register) accredited – an award that helps to streamline procurement processes.
- **Cyber Essentials** certified – a government-backed programme that provides security assurance of a supplier's digital infrastructure.



Discover how we can **optimise** operational performance

**Contact** [chris@nicofe.com](mailto:chris@nicofe.com)



**Nicofe Materials**

Unit 8D, Torr View, Torr Quarry Industrial Estate, East Allington, Totnes TQ9 7QQ

**01548 858770 | [sales@nicofe.com](mailto:sales@nicofe.com) | [www.nicofe.com](http://www.nicofe.com)**